



# Peeled round steel bars

**Sales Office:**

Riva Stahl GmbH - Wolfgang-Küntschers-Str. 18 - 16761 Hennigsdorf

**Tel:** +49 3302.806.13.243 - **Fax:** +49 3302.806.13.238

**Email:** [sales.quality@rivagroup.com](mailto:sales.quality@rivagroup.com)

Revision 08/2014



# Peeled round steel bars

Revision: 08/2014 - Page 2 of 3

## DIMENSIONS (DIAMETER)

8 up to 80 mm, tolerance according to DIN EN 10278, IT 9 or higher

## LENGTHS AND LENGTH TOLERANCES FOR STEEL PEELED FROM THE BAR, DRAWN OR GROUND

Production lengths	4500 up to 6500 mm $\pm$ 500 mm Other lengths upon agreement
Stock lengths	3000 mm -0, +200 mm 6000 mm -0, +200 mm
Precision lengths	3000 up to 6500 mm with tolerances of +/- 100 mm up to +/- 5 mm upon agreement Lengths up to 7000 mm and smaller length tolerances upon agreement Other bar lengths from 800 up to 7200 mm on request

## BAR END FINISHING

Sheared, abrasive cut-off or sawed (standard)  
Chamfered, flattened, chamfered and flattened, on one or on both sides

Definition of the chamfer:  
- chamfer angle: 30°, 45°, 60°  
- chamfer eccentricity: max. 0,2 mm  
- chamfer width: max. 10 mm

## STRAIGHTNESS

According to DIN EN 10278

## TECHNICAL TERMS OF SUPPLY

According to DIN EN 10277

Bright steel products

## GRADES

Steel grades are supplied according to the following standard:

EN 10277	Bright steel products
EN 10016-1 -4	Non-alloy steel for drawing and/or cold rolling
EN 10025-1 -6	Hot rolled products of structural steels
EN 10083-1 -3	Steels for quenching and tempering
EN 10084	Case hardening steels
EN 10085	Nitriding steel
EN 10087	Free cutting steels
EN 10089	Hot rolled steels for quenched and tempered springs
EN 10113	Hot-rolled products in weldable fine grain structural steels
EN 10263	Steel rod, bars and wire for cold heading and cold extrusion
EN 10269	Steels and nickel alloys for fasteners with specified elevated and/or low temperature properties
EN 10273	Hot rolled weldable steel bars for pressure purposes with specified elevated temperature properties
DIN 17212	Flame and Induction Hardening Steels

Other grades upon agreement, even modified and/or without standard.  
Electromagnetically stirred steel (mould stirring) is supplied on request.



# Peeled round steel bars

Revision: 08/2014 - Page 3 of 3

## QUALITY TESTS

Surface defects	Eddy-current testing (8 up to 80 mm), bars only Defect detection    Depth $\geq 0.2$ mm Length $\geq 10.0$ mm 100% visual inspection (8 up to 80 mm)
Core defects and near-surface defects	Supersonic test (18 up to 80 mm), bright steel bars only Defect detection:    Diameter $\geq 10.7$ mm Length $\geq 10.0$ mm The probe-to-specimen contact occurs with water and corrosion inhibiting additives.
Identity control	Spectroscopy Spark test Eddy-current test (8 up to 80 mm)

## ACCEPTANCE, TEST CERTIFICATES

Test certificates according to EN 10204.

Acceptance by institutions like TÜV; Germanischer Lloyd; SGS; Lloyd's Register of Shipping; Deutsche Bahn AG.

## WEIGHTS

Bars (in bundles): 1000 up to 3000 kg

## CONSERVATION

Temporary protection against corrosion through slushing oil

## BINDING, PACKAGING

Binding	with steel strap 32 x 0,8 mm with PE foil or crêpe-paper underneath
Packaging	- PE-foil, crêpe-paper and fibre-reinforced, crack resistant foil - in crates
Packaging upon agreement only.	

## LABELLING

Each bundle has two labels with the following data: customer, order number, bundle number, steel grade, state of supply, heat number, diameter, tolerance, length (only for bars), weight.

Different data upon agreement.

Colour-marking of bar end faces upon agreement.